import en export van hardhout


## **Quality description of European oak**

09.09.14


#### A) Quality requirements of Class 1:

- a) Healthy knots till 10 mm allowed on one side allowed. The other side the knots can be 20 mm. No dead knots allowed.
- b) Sapwood: maximum 25 mm on each side allowed (see pictures).


Option 1:




Option 2:








- c) No full center allowed (see pictures)
- d) One center strip of 50 cm long on one side of the board allowed (see pictures)
- © Full center is not allowed.



(d) Center stripes of 50 cm are allowed.



### B) Quality decription of 39 and 51 mm thickness, European oak (3 qualities)

1) <u>¾ sides defect free</u>, no center, no center stripes, 10 mm sapwood on on one sides (so one side knots are allowed)

### 2) Mix-quality:

- maximum knot size is 70 mm
- maximum knot size of dead knots is 20 mm
- cracks smaller than 100 mm
- sapwood < 25 mm per side
- no yellow discolouration, insect attacks and bark/wane allowd
- No Center stripes allowed!
- No Center allowed!!!

Houthandel Wijers


De Meent 1 6871 TR Renkum
t 0317 - 310698 f 0317 - 310201
info@houthandelwijers.nl

IBAN nummer: NL76RABO 0385053282 BTW nummer: NL853298580B01


# **Houthandel Wijers**

import en export van hardhout

© Full center is not allowed.



## (d) No center stripes allowed.



## 3) Rustical-quality:

- center allowed, at max 30 % of the boards
- center stripes allowed
- big knots allowed
- one dimension per parcel.
- sapwood < 25 mm per side

## C) Quality decription of 26 mm mix-quality, European oak

- core, center stripes of 1/3 length of the board allowed on 15 % of the boards!
- maximum knot size is 70 mm
- maximum knot size of dead knots is 20 mm
- cracks smaller than 100 mm
- sapwood < 25 mm per side, max on 20 % of the boards